

Technical Data Sheet



Date Feb 2015

Replaces July 2014

Flooring & protective Finishes

SURECHEM VE - Highly durable Industrial Floor Topping

GENERIC TYPE:

A highly chemical resistant vinyl ester resin based aggregate filled topping for durable floor toppings

PROPERTIES /FEATURES:

- Surechem VE is an extremely hard wearing monolithic 6.5 to 9mm thick vinyl ester resin based flooring system.
- Surechem VE has been specifically designed to provide excellent all round chemical resistance at both end of the pH scale i.e. concentrated acid and alkali compounds.
- Exceptional impact, abrasion and wear resistance.
- Excellent adhesion to most substrates (refer Surechem specification).
- Can be used to form coves, plinths and follow complex curves and shapes.
- Good weathering resistance. May chalk and exhibit slight discolouration when subjected to prolonged UV exposure. This will, however, not detract from its general durability and chemical resistance.
- Chemical resistance and general physical properties can be improved by POST CURE TREATMENT.
- Almost any surface finish can be obtained, from a smooth easily cleaned, to a coarse non-skid texture.
- Good resistance to high temperatures and thermal shock.
- Will not support bacteria or fungal growth.
- It is not moisture permeable.
- Minimum application temperature +12°C.

TYPICAL PHYSICAL PROPERTIES OF CURED TOPPING:

- Compressive strength (50mm cube): 90MPa
 - Tensile strength: 22 MPa
 - Moisture absorption: 0.04%
 - Flexural strength: 38 MPa
 - Flexural modulus: 17 GPa
 - Weight per m² @ 6.5mm thick: 15.0kgs
 - Temperature resistance: up to 100°C
- (Note: temperature resistance is lowered when combined with certain chemical solutions. Refer to Nuplex Industries for specific advice.)

SUGGESTED USES:

- On Floors, walls, upstands, coves, plinths etc where a very high degree of all round chemical resistance is required.
- Sewage & wastewater facilities for liquid protection and gas-phase (Hydrogen Sulphide) protection.
- Chemical storage bunds.
- Process floors where hygiene is essential.
- Surechem VE topcoat is also used to provide extra durability as a replacement for STZ topcoat in the Sureshield floor topping system.

Australia A Division of Nuplex Industries Limited
www.nuplexconstruction.com.au

New Zealand A Division of Nuplex Industries (NZ) Limited
Auckland T: +64 9 5836544 F: +64 9 5253709

This information appearing in this Document (Details) concerning the product which is the subject of the Document (Product), is either based on present technical knowledge and tests done by Nuplex or tests done by, and data supplied from third parties including you, the customer. Since the actual use by you and by others of the Product is beyond the control of Nuplex, no warranty or representation, express or implied is made by Nuplex regarding the suitability for such use, nor does Nuplex accept any liability arising out of the use by you of other products or materials, whether third party or not, that may be referred to in this Document. Nuplex recommends that you carry out your own tests as to the suitability of the Product for your purpose, regarding which you accept full responsibility. In addition, if any of the Details appearing in the Document are based upon tests done by, and/or data supplied by any third party, Nuplex provides no warranties or representations in connection with those Details and you, the customer waives any right you may have against Nuplex in connection with the accuracy, completeness or otherwise of the Details. The information in this Document is not to be construed as absolutely complete or accurate since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations affecting use of the Product. Nuplex does not provide any warranty or representation to you that the Product does not infringe the intellectual property rights of any third party. All orders accepted shall be subject to the standard conditions of sale of Nuplex, which are on the back of our invoice. In accepting the Product you, the customer acknowledge and agree:

- The Product is or may be of a hazardous nature and that you, the customer, are responsible for the disposal of the container housing the Product in accordance with the requirements and regulations of the relevant supervising government.
- The Product has a limited shelf life and must be stored strictly in accordance with the guidelines and specifications related to it.
- Where the Details relate to Product tested by Nuplex, those Details are indicative only, regarding which there may be batch-to-batch variation.
- Nuplex gives no warranty or representation as to the applicability for the particular use by you, the customer, of the Product and you the customer shall be responsible for ensuring that the Product is fit for your intended use.
- Nuplex's liability for breach of any term, condition, guarantee or warranty (express or implied and concerning the information in this Document or the Product more generally) including any liability for direct or indirect consequential loss (including indirect loss of profits), is limited to the maximum extent permitted by law and, at Nuplex's election, to either replacing or repairing the goods or paying the cost of replacing or repairing the goods, or in the case of services, supplying the services again.

www.nuplexconstruction.co.nz • ncpsales@nuplex.com • FreePhone: 0508-882288 • FreeFax: 0508553344

Not recommended

- Application to uncured or green concrete (minimum recommended cure period 28 days).
- Application to unstable substrates.
- Application to damp surfaces or when surface dew point has been reached. Maximum moisture content – timber 12%, Concrete 75% RH.
- Application where fumes may contaminate adjacent foodstuffs.
- Application over existing coatings/toppings without approval by Nuplex Industries Ltd.
- Always use Surechem VE topcoat. (VE resin surface will be tacky).

Storage of materials: Store at normal ambient temperatures (neither hot nor cold); never in direct sunlight.
(storage in shipping containers will generally result in over heating)..
(Hot vinyl ester will cure very rapidly). (cold vinyl ester will not cure fully).

Mixing and site conditions: Shield mixing area and work site floor areas from direct sunlight and UV. Directly impacting UV light will rapidly accelerate vinyl ester curing.

Surface preparation: Concrete is to be clean and dry. Heavily shotblast, very coarse grinding or scabbling is required.
Surface profile CSP 7 or 8 is needed.

Material Pre-preparation: (promote & catalyse)

New Pails of Surechem VE resin & Surechem VE topcoat are marked as unpromoted. Nuplex supply the VE in 20 ltr pails with open top lids enabling the Cobalt to be mechanically mixed into the resin base. Buy another catalyst dispenser and mark it for Cobalt use only. The cobalt can be added up to 12 hours prior to use. Always add Cobalt first, mix and then add catalyst. Never mix Cobalt and catalyst. Pre-train staff. The lids are marked as un-promoted – tick or mark once promoted. **Good Trade Practice: - Train staff & mix cobalt and mark all resin in a separate operation on the same day as use. Then take the promoted material to the workface for catalyst addition.**

Surechem VE Resin 0.3%. or 60grams GRAMS COBALT TO ADD PER 20Kg.

Surechem VE Topcoat 0.3%. or 30grams GRAMS COBALT TO ADD PER 10Kg.

Check the Cobalt's age and stability by doing a TRIAL prior to work start. Promote at the correct level, then add a 1.5% catalyst to check that the reaction starts. Even if high catalyst levels are added, unpromoted resins will not cure. This trial can also be used if confusion occurs about Cobalt addition.

Be well organised and train staff clearly in the promotion and catalysation processes. Mistakes are costly.

Mixing Method

Concrete mixer, paddle mixer, Hobart mixer (small quantities only). (Care must be taken to avoid air entrainment.)

APPLICATION: Method

1. STZ Primer: Catalyse prior to use. Apply with Brush or roller. 4m²/ LT
2. Surechem VE Topping: Prepare as above ; then Hand trowel using glass & steel floats to form floors, coves, drain sides, etc.
3. Surechem VE Topcoat: Brush, roller (promote as above). 4m²/ Lt

*****Caution***** System must be topcoated with Surechem VE topcoat for full cure.

Full details of coves, drains, upostands etc are on the Nuplex website at:
http://www.nuplexconstruction.co.nz/pdf/Details_resin-floor-toppings.pdf

COVERAGE RATES: (6.5mm topping/m²)

Nuplex STZ Primer:	0.25kg/m ²
Surechem VE Resin:	2.50kgs
STZ flooring silica Gap Graded Aggregates: (resin : aggregates : 1 : 5.2)	13.0kgs
Surechem VE Topcoat: (level of catalyst dependant on temperature)	0.25kg/m ²

Note: The above rates are theoretical and do not take into account losses through surface irregularities, mixing and application.

PROMOTER: See above; variations on the level added as stated above are permitted with Nuplex consent in certain environmental conditions.

CATALYST: NB: Promote both resin and topcoat before use.
Then use Nuplex VE Catalyst only. Use 1.5 - 2.0% on resin weight depending on temperature.

RETARDER: Where extended working time is required Nuplex VE Retarder may be incorporated in the resin prior to the addition of catalyst. There are Maximum recommended addition rates.

THINNING: Not recommended. If necessary consult Nuplex Industries Ltd for advice.

CLEAN UP: Acetone. Styrene. Lubricate equipment, tools (mixer, barrow, trowels etc) using styrene monomer only.

CURE AND DRY TIMES @ 25°C: (Excluding the use of retarder) 1.5% MEKP catalyst

Workable pot life:	10-20 minutes
Hard Dry:	3 hours
Light Foot Traffic:	6 hours
Full use (unrestricted):	18 hours
Maximum recoat:	24 hours
(Requires special preparation after this period)	

CAUTION: Residual fumes may contaminate foodstuffs.

- Provide adequate ventilation during application and cure.
- VE catalyst is highly corrosive. Protect eyes, skin etc.
- Do not mix or store MEKP (catalyst) or promoter together – explosion and/or fire may result.
- Wear suitable protective respirator and clothing when using this product.
- Products are highly flammable.
- Erect "No Smoking" signs.
- No welding or naked flames permitted during installation.
- Have fire extinguishers readily available.
- Refer MSDS on line www.nuplexconstruction.co.nz

SHELF LIFE: 12 months in unopened containers.
Maximum useful life 12 months (check suitability with Nuplex Industries before use).

CHEMICAL RESISTANCE @ 25°C (Ambient)

Acetic Acid	70%	NC
Brine	Sat	NC
Citric Acid	Sat Soln	NC
Distilled Water	All	NC
Hydrochloric Acid	37%	NC
Hydrofluoric Acid	20% (may attack silica aggregates)	EF
Hydrogen Peroxide	35%	NC
Hydrogen Sulphide	All	NC
Lactic Acid	All	NC
Nitric Acid	30%	NC
Nitric Acid	40%	EF*
Oxalic Acid	Sat	NC
Phosphoric Acid	85%	NC
Caustic, Sodium Hydroxide	50%	NC
Sodium Hypochlorite	(Refer Nuplex Industries for a specific recommendation)	
Sulphuric Acid	70%	NC
NR	Not recommended	
NC	Not corrosive	
EF	Evaluate further	
*	Staining may result	

Solutions are Aqueous unless otherwise stated

NOTE:

The table represents a guide only. Variable which may under extreme conditions, influence the chemical or corrosion resistance are:

1. Temperature of chemical concentration.
2. Intermittent or continuous contact.
3. Application under adverse conditions.
4. Risks of evaporation from chemical spillages causing concentration to rise adversely.
5. Good service may be expected where NR or EF is specified if exposure is intermittent or limited to occasional splash spill or fumes. Refer to Nuplex Industries Ltd for specific advice on this, or chemical contamination other than those listed.
6. Chemical resistance and general physical proprietary can be improved by post cure treatment (refer to Nuplex Industries Ltd for specific advice).

